



COMMERCIAL PRODUCT SPECIFICATIONS

Wollastonite W-0/2

PARAMETER	STANDARD VALUE	METHOD
Granulometry (*)	0-2 mm.	ISO 2395-1990 ISO 565-1990 ISO 3310-1:1990
Maximum Humidity	2%	ISO 3234-1975
Lost On Ignition	6,3 %	ITC- E-13
SiO₂	48,4 %	XR Fluorescence. Program calibrated with samples analyzed in certificated laboratories.
CaO	30,4 %	
Al₂O₃	6,1 %	
Fe₂O₃	2,2 %	
MgO	1,9 %	
Na₂O	1 %	
K₂O	1,4 %	
TiO₂	0,3 %	
P₂O₅	0,13 %	
MnO₂	0,08 %	

(1) The size of 98% of particles, expressed in weight, is less than 2 mm.

Aldea del Obispo, July 20, 2018



D. David Esteban Martínez
Executive Director



D. Álvaro Cuesta Martín
Quality Manager